

EPOLENE® E-10 Polymer

Application/Uses

- Automotive
- Building and Construction
- Hot Melt Adhesives
- Pressure Sensitive Adhesives
- Solventborne Adhesives
- Waterborne Adhesives
- Wax Modification

Attributes

- Imparts slip resistance, durability, and toughness to floor finishes
- Oxidized to provide functionality
- Produces stable water based solutions
- Oxidized low density polyethylene

Product Description

EPOLENE® E-10 polymer is an oxidized low molecular weight polymer used in emulsifiable applications. The low molecular weight and low softening point contribute to the production of stable, low color emulsions by both atmospheric (wax to water) and pressure emulsification methods. In water based emulsion floor finishes, it imparts good slip resistance, toughness and durability to the polish film.

Typical Physical Properties

Property ^a	Test ^b Method	Typical Value, Units ^c
Acid Number	D-1386	14-18.5 mg-KOH/g
Penetration Hardness	D-5	2 dmm
Mettler Drop Point	D-6090	105 °C
Brookfield Viscosity @ 125 °C	D-4287	650-1,200 cP
Yellowness Index	D-313	≤ 4.0

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

COMMENTS

Properties reported here are indicative values only. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

Packaging

EPOLENE E-10 polymer is supplied as free-flowing pellets, packaged in multiwall paper bags with a polyethylene coated inner liner [22.67 kg (50 lb) net weight]. Many EPOLENE polymers are also shipped in a variety of bulk containers. EPOLENE E-10 polymer is also available in powder form as EPOLENE E-10P polymer.

Storage

The useful life of this product can be affected by storage and handling conditions. Product should be stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination. First in first out (FIFO) inventory management is recommended.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION

2801 Post Oak Blvd Suite 600 Houston, Texas Customer Service: 1-800-545-9577

March 2019

EPOLENE® is a trademark of Westlake Chemical Corporation.

b Unless noted otherwise, the test method is ASTM.

c Units are in SI or US customary units