

# Keltan<sup>®</sup> 3960

## Product Description

Semi crystalline ethylene-propylene rubber with very high ENB (ethylidene norbornene) content and a low Mooney viscosity. The very high ENB content enables very fast and efficient network formation resulting in excellent physical properties.

Typical application areas are high hardness automotive profiles and corner moulds.

## Supply Form

Standard bales.

## Raw Material Properties

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+8) 100°C	54	MU	ISO 289
Ethylene content	56	wt %	ASTM D 3900
ENB content	11.0	wt %	ASTM D 6047
Molecular weight distribution	Medium		ARLANXEO

## Other Product Features

Property	Typical Value
Specific gravity	0.86 kg/dm <sup>3</sup>
Stabilizer	non-staining
Packaging	Cardboard box; LDPE bale wrap; 36 standard bales (900 kg).

# Keltan<sup>®</sup> 3960

<b>Storage Life/Conditions</b>	The product should be stored dry and at temperature < 30 °C. Exposure to light has to be avoided.
<b>Shelf life</b>	36 months from date of production stored at above mentioned conditions.
<b>Product Safety</b>	Relevant safety data and references as well as the possibly necessary warning labels are to be found in the safety data sheet.

KELTAN<sup>®</sup> is a Registered Trademark of ARLANXEO Netherlands B.V.

**Health and Safety Information:** Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the ARLANXEO products mentioned in this publication. For materials mentioned which are not ARLANXEO products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, *e.g.*, *material safety data sheets and product labels*. Consult your ARLANXEO Corporation representative or contact the Product Safety and Regulatory Affairs Department at ARLANXEO.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. As with any product, use of the products mentioned in this publication in a given application must be tested (including field testing, etc.) by the user in advance to determine suitability.

Issue number: LXS 12 / Date of issue: January 15, 2020 / Previous issue from November 28, 2019 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.