



KEY ADVANTAGES


- Highly active antioxidant
- Low volatility
- Low staining characteristics
- Does not activate scorch nor cause bin cure

APPLICATIONS

- Provides resistance to heat and flex fatigue in rubber applications such as belts and industrial rubber goods. Very effective in polychloroprene
- Stabilization of synthetic polymers, latices and lubricants
- Protection of medium and high voltage polyethylene cables
- Protection of adhesives

WINGSTAY® 29A

Mixed para oriented styrenated diphenylamines



TYPICAL PROPERTIES

Physical form	Clear yellow viscous liquid (WINGSTAY 29A Powder is available as 70% active on inert silica)
Specific gravity	1.080
Average molecular weight	390
Viscosity @ 25°C (mPa.s)	35,000
Refractive index @ 25°C	1.639
Bound styrene/diphenylamine molar ratio	2.1
Solubility	Soluble in aromatics, Ketones, and alcohols, insoluble in water

PACKAGING, HANDLING AND STORAGE

- Packaging: **WINGSTAY 29A Liquid**: Open head metal drum with two sealable bungs. (2 in. and 3/4 in.). Dimensions (mm): Diameter: 610, H: 915. Net weight: 200 kg (441 lbs). **WINGSTAY 29A Powder**, 70% active: 24 x 25 kg cardboard boxes stretch wrapped on a pallet. Dimensions (mm): L: 1220, W: 820, H: 1260. Net weight: 567 kg (1250 lbs).
- Storage: Store in dry, well ventilated area away from direct sources of heat or sun.
- Please read the material safety data sheet (MSDS) prior to use. A copy is available on www.quickfds.com or may be obtained by contacting your Customer Service Representative.

NOTE: Although the data supplied above is believed to be accurate, each user is advised to make an independent determination as to whether the described product(s) is/are appropriate for a particular use or application, whether such use will comply with all applicable laws or regulations, or whether such use will infringe the intellectual property rights of third parties.

www.omnova.com



Americas

World Headquarters
175 Ghent Road
Fairlawn, OH 44333 USA
PHONE +1 330 869-4323
FAX +1 330 869-4338
CUSTOMER SERVICE +1 888 253-5454
EMAIL pccustserv@omnova.com

Europe / Middle East / Africa / India

14, avenue des Tropiques
Z.A. de Courtaboeuf 2 - Villejust
91955 Courtaboeuf Cedex
France
PHONE +33 (0) 1 69 29 27 00
FAX +33 (0) 1 69 29 27 01

Asia

Unit 09-11, 7th Floor,
Greenland Riverside International Center
596 Long Hua Middle Road, Xu Hui District
Shanghai, 200032, China
PHONE +86 (21) 6473 2525
FAX +86 (21) 5421 1766

ALL OMNOVA PRODUCTS AND SERVICES ARE OFFERED AND SOLD SUBJECT TO THE OMNOVA STANDARD TERMS AND CONDITIONS OF SALE AGREEMENT SET FORTH AT WWW.OMNOVA.COM.

All trademarks - OMNOVA Solutions.

© 2014 OMNOVA Solutions

January 2014